NORYL™ RESIN 731

REGION ASIA

DESCRIPTION

PPE+PS blend. Unfilled. UL94 HB rated. Low water absorption. Hydrolytic stability. Dimensional stability. Suitable for fluid engineering applications: valve components, water pump housings, etc. This grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HN731A.

TYPICAL PROPERTY VALUES

Revision 20170531

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	45	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	30	%	ASTM D 638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	40	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	70	%	ISO 527
Tensile Strain, break, 50 mm/min	70	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	800	J/m	ASTM D 4812
Izod Impact, notched, 23°C	150	J/m	ASTM D 256
Izod Impact, notched, -30°C	120	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	55	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	60	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	55	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	16	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	11	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m²	ISO 179/1eA
THERMAL			

© 2017 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	133	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	110	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	124	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.3E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	133	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	112	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	11	g/10 min	ASTM D 1238
Water Absorption, 23°C/24hrs	0.13	%	ISO 62-1
Moisture Absorption, 50% RH, 24hrs, Equilibrium	0.04	%	ISO 62-4
Melt Volume Rate, MVR at 280°C/5.0 kg	12	cm^3/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 310	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	270 – 310	°C	
Middle - Zone 2 Temperature	260 – 305	°C	
Rear - Zone 1 Temperature	250 – 300	°C	
Mold Temperature	75 – 105	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.
It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.
Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

© 2017 Copyright by SABIC. All rights reserved

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.

© 2017 Copyright by SABIC. All rights reserved